

## PRODUCT DATA

### HARD HAT® AEROSOLS FLUOR TOPCOATS 2200

#### DESCRIPTION

RUST-OLEUM® Hard Hat Aerosols Fluorescent Topcoats 2200 are based on a fast drying acrylic resin. The products are based on special fluorescent pigments and are lead- and chromate free.

#### RECOMMENDED USES

RUST-OLEUM Fluorescent Topcoats 2200 should be applied over RUST-OLEUM Hard Hat 2190 Flat White; for exterior applications it is recommended to recoat Fluorescent Topcoats 2200 with RUST-OLEUM Hard Hat 2500 Clear.

RUST-OLEUM Fluorescent Topcoats 2200 are intended for safety marking or signalling. RUST-OLEUM Fluorescent Topcoats 2200 should be used in light industrial exposures, normal humidity and interior applications.

#### TECHNICAL DATA

Appearance:	Flat/fluorescent
Colour:	See colour card
Propellant:	Dimethyl ether
Recommended film thickness:	25 µm dry, equals averagely 100 µm wet
VOC-content:	653 g/l

<b>Drying times</b>	20°C/50% r.v.
To touch:	15 minutes
To handle:	30 minutes
To recoat:	After 1 hour
Full hardness	3 days

Heat resistance: 100°C (dry heat)

#### Coverage

Theoretical: 2.1 m<sup>2</sup> per spray can at 25 µm dry

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

#### SURFACE PREPARATION

Remove dirt, grease, oil and all other surface contaminants by appropriate means. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

#### DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

#### APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

Rust-Oleum Netherlands B.V.  
Braak 1, 4704 RJ  
P.O. Box 138, 4700 AC  
Roosendaal, The Netherlands  
T +31 (0)165 593 636  
F +31 (0)165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)  
[www.rust-oleum.eu](http://www.rust-oleum.eu)

N.V. Martin Mathys S.A.  
Kolenbergstraat 23  
3545 Zelem  
Halen, Belgium  
T +32 (0)13 460 200  
F +32 (0)13 460 201  
[info.be@ro-m.com](mailto:info.be@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

Rust-Oleum France S.A.S  
11, Rue Jules Verne, B.P. 60039  
95322 St-Leu-la-Forêt Cedex  
France  
T +33 (0)1 30 40 00 44  
F +33 (0)1 30 40 99 80  
[info.fr@ro-m.com](mailto:info.fr@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

Rust-Oleum UK Ltd.  
Rotterdam House  
116 Quayside  
Newcastle  
NE1 3DY  
United Kingdom  
T +44 (0)2476 717 329  
F +44 (0)2476 718 930  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)  
[www.rust-oleum.eu](http://www.rust-oleum.eu)

## PRODUCT DATA

### HARD HAT® AEROSOLS FLUOR TOPCOATS 2200

#### REMARKS

Fluorescent topcoats should be applied on a white substrate for maximum brightness.  
At UV-light exposure the colour tends to fade, the speed of fading is directly proportional to the dry film thickness and the intensity of the UV-light.

#### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

#### SHELLIFE / STORAGE CONDITIONS

3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Rust-Oleum Netherlands B.V.**  
Braak 1, 4704 RJ  
P.O. Box 138, 4700 AC  
Roosendaal, The Netherlands  
T +31 (0)165 593 636  
F +31 (0)165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)  
[www.rust-oleum.eu](http://www.rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Halen, Belgium  
T +32 (0)13 460 200  
F +32 (0)13 460 201  
[info.be@ro-m.com](mailto:info.be@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

**Rust-Oleum France S.A.S**  
11, Rue Jules Verne, B.P. 60039  
95322 St-Leu-la-Forêt Cedex  
France  
T +33 (0)1 30 40 00 44  
F +33 (0)1 30 40 99 80  
[info.fr@ro-m.com](mailto:info.fr@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

**Rust-Oleum UK Ltd.**  
Rotterdam House  
116 Quayside  
Newcastle  
NE1 3DY  
United Kingdom  
T +44 (0)2476 717 329  
F +44 (0)2476 718 930  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)  
[www.rust-oleum.eu](http://www.rust-oleum.eu)